

## VELOURS MOLIÈRE

### TECHNICAL DATA SHEET

January 2016

The heaviest cotton velvet with dense upright pile and rich colour.

» <b>ARTICLE CODE</b> 1218 0140 #	» <b>WIDTH</b> 140 cm	» <b>LENGTH</b> ± 45 m	» <b>WEIGHT</b> 600 g/m <sup>2</sup>
--------------------------------------	--------------------------	---------------------------	---


» <b>COMPOSITION</b> 100% CO	» <b>CARE INSTRUCTIONS</b> 
---------------------------------	---

» <b>FLAME RESISTANCE</b> NFP 92-503 (1995) BS 5867 PART 2 TYPE B (2008) NEN EN ISO 6941 DIN 4102	CLASS M1 PASS PASS CLASS B1
---	--------------------------------------

» <b>ABRASION RESISTANCE</b> ISO 12947-2 & 4: 1998/Cor.1.2002 35 000 cycles: note 4	» <b>TENSILE STRENGTH</b> ISO 13934-1: 1999 Warp: 932 N • Weft: 812 N	» <b>WRINKLE RECOVERY OF FABRICS</b> AATCC 66: 200 Warp: 104° • Weft: 110° • Total: 214°
---	---	--

» <b>RESISTANCE TO PILLING</b> ISO 12945-2: 2000 10 000 cycles: note 4-5	» <b>TEAR STRENGTH</b> ISO 13937-3: 2000 Warp: 21.6 N • Weft: 21.6 N	» <b>COLOUR FASTNESS TO LIGHT</b> ISO 105-B02-1994: Amd 2: 2000 Note 6
--	--	--

» **AVAILABLE COLOURS**



0201


## VELOURS MOLIÈRE

### TECHNICAL DATA SHEET

January 2016

#### SOUND ABSORPTION

full box pleated curtain • 15 cm from the wall



f(Hz)	$\alpha_s$
100	0,17
125	0,15
160	0,17
200	0,24
250	0,36
315	0,50
400	0,62
500	0,62
630	0,59
800	0,60
1000	0,58
1250	0,56
1600	0,54
2000	0,55
2500	0,56
3150	0,58
4000	0,58
5000	0,59

ISO 11654

$\alpha_w = 0,60$